

557595

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
28 October 2004 (28.10.2004)

PCT

(10) International Publication Number
WO 2004/092080 A1

(51) International Patent Classification⁷: **C03B 3/02**,
23/20, 31/00

(21) International Application Number:
PCT/US2004/011279

(22) International Filing Date: 12 April 2004 (12.04.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/462,417 11 April 2003 (11.04.2003) US

GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant and
(72) Inventor: HAUN, Michael, Joseph [US/US]; 5819 La Cuesta Drive, Santa Rosa, CA 95409 (US).

Published:
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PRODUCTS MADE FROM LAMINATED-GLASS WASTE

(57) Abstract: The invention provides a low-cost energy-saving method of manufacturing a glass product directly from laminated glass waste without having to crush the glass and separate the plastic interlayer, even when the glass is cracked. The method comprises heating laminated glass to fuse the glass layers and broken pieces of glass into a glass product. The plastic interlayer initially acts as a binder to hold the glass pieces together, but is then burned out during the heating prior to fusing the glass pieces together. Fusing laminated glass with cracked glass produces unique textures and patterns in the glass product. Coatings can also be applied to produce different colors and patterns in the glass product.



WO 2004/092080 A1